







Most suitable for silos and confined areas of grains, sugar, fertilizers, among others, where there is a risk of electrical discharges caused by the accumulation of static charge. Through the addition of conductive loads, **Duramaxx AST** has antistatic properties, providing security or high fluidity for the systems where it is used.

GENERAL PROPERTIES

Characteristics	Method	Units	Values
Density	ASTM D792	g/cm³	0,93
Average Molecular Weight		g/mol	8.0 x 10 ⁶
Water Absorption	ASTM D570	%	<0,01
Flammability	UL94	-	HB

MECHANICAL PROPERTIES

Characteristics	Method	Units	Values
Tensile Strenght at Yield	ASTM D638	Мра	21
Tensile Strenght at Break	ASTM D638	Мра	>30
Elongação até a ruptura	ASTM D638	%	>200
Flexural Modulus of Elasticity	ASTM D790	MPa	>700
Flexural Strenght	ASTM D790	MPa	20
Abrasion Resistance (Sand Slurry Test)	ABNT NBR 14922	-	24
IZOD Impact (notched)	ASTM D256	-	No Break
Compressive Strenght, 10% deformation	ASTM D695	MPa	20
Compressive Modulus of Elasticity	ASTM D695	Мра	480
Hardness	ASTM D2240	Shore D	65
Static Friction Coefficent	ASTM D1894	-	0,13
Kinetic Friction Coefficient	ASTM D1894	-	0,11

THERMAL PROPERTIES

Characteristics	Method	Units	Values
Melt Temperature	ASTM D3418	Ĵ	133
Thermal Condutivity @ 23°C	ASTM D177	W / (m * K)	0,4
Specific Heat @ 23°C	ASTM E1269	Cal∕g°C	0,48
Coefficient of Linear Expantion (30 - 100°C)	ASTM D696	10-4/°C	1,5
Service Temperature (Continous, in air)	Média	Ĵ	90
Service Temperature (short period)	Média	°C	130
Heat Deflexion Temperature	ASTM D648	°F	116

ELECTRICAL PROPERTIES

Characteristics	Method	Units	Values
Dielectric Strenght	ASTM D149	kV/cm	900
Dielectric Constant @ 1Khz	ASTM D150	-	2,3
Surface Resistivity	ASTM D257	Ω	10 ⁶ - 10 ⁹
Dissipation Factor, 10–Hz	ASTM D150	-	-

³⁻ Does not contain the substance Bisphenol A (BPA, CAS# No.80-05-7)
4- The content of this Data Sheet replaces revisions published for this product.



¹⁻ The mentioned values in this report can be changed at any moment without Baron previous comunication.
2 -The informations presented in this data sheet reflects typical values of the resin specificatios, and tests in our laboratories, and should not be considered as absolute or warranted values. Only the properties and values mentioned on the certificate of quality are considered as guarantee of the product.